



CENTRO DI RICERCA E SPERIMENTAZIONE
PER L'INDUSTRIA CERAMICA

Bologna, 10/12/2018

*FRIANOVO CERAMIC
FACTORY LLC
141147, Russia, MR,
Shelkovsky Distr.*

TEST LABORATORY

TEST REPORT No. 7771/18

Requested by:	FRIANOVO CERAMIC FACTORY LLC 141147, Russia, MR, Shelkovsky Distr.
On (date):	19/10/18
For the sample marked:	"BRICKS".

The results reported relate only to the samples tested.

No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision.

The reproduction of this test report is only authorized in the form of a complete photographic facsimile.

Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages this cover included.



Description of the sample:	Glazed ceramic tiles 30 x 60 x 0.9 cm marked "BRICKS".
Manufacturer:	-----
Sampling details	
- Where:	-----
- Date:	-----
- By whom:	CUSTOMER
- How (methods):	-----
Date of receipt in laboratory:	05/11/18

TESTS PERFORMED :

		Date of starting	Date of ending
<input checked="" type="checkbox"/>	DIN 51097 (92) Slip resistance	03/12/18	03/12/18




DIN 51097 (92) - Slip resistance

- Size of the tested surface (m) 0.50 x 1.00
- Joint width (mm): -----
- Grout: -----

OPERATIVE CONDITIONS

Fixing scheme



RESULTS

- Average slip angle:

15°

CLASSIFICATION (BGI/GUV-I 8527- 2010)

- Evaluation group:

A

Pietro Bruzzi
Technical verification



Prof. Maria Chiara Bignozzi

Director