



CENTRO DI RICERCA E SPERIMENTAZIONE
PER L'INDUSTRIA CERAMICA

Bologna, 10/12/2018

*FRIANOVO CERAMIC
FACTORY LLC
141147, Russia, MR,
Shelkovsky Distr.*

TEST LABORATORY

TEST REPORT No. 7746/18

Requested by:	FRIANOVO CERAMIC FACTORY LLC 141147, Russia, MR, Shelkovsky Distr.
On (date):	19/10/18
For the sample marked:	"FINWOOD".

The results reported relate only to the samples tested.

No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision.

The reproduction of this test report is only authorized in the form of a complete photographic facsimile.

Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages this cover included.



Description of the sample:	Glazed ceramic tiles 18.5 x 60 x 0.9 cm marked "FINWOOD".
Manufacturer:	-----
Sampling details	
- Where:	-----
- Date:	-----
- By whom:	CUSTOMER
- How (methods):	-----
Date of receipt in laboratory:	05/11/18

TESTS PERFORMED :

		Date of starting	Date of ending	
<input checked="" type="checkbox"/>	DIN 51130 (06/2004)	Determination of the anti - slip properties – Workrooms and fields of activities with raised slip danger, walking method – ramp test	04/12/18	04/12/18


DIN 51130 (06/2004)- Determination of the anti - slip properties – Workrooms and fields of activities with raised slip danger, walking method – ramp test

Surface characteristics

- Smooth
- Profiled
- Structured
- Rough

OPERATIVE CONDITIONS

Fixing scheme



RESULTS

Average total acceptance angle:

6.5°

Movement area (cm³/dm²):

CLASSIFICATION (BGR 181- 10/2003)

Group of anti - slip properties:

R9

Movement area evaluation group:

Pietro Bruzzi
Technical verification



Prof. Maria Chiara Bignozzi

Director