



CENTRO DI RICERCA E SPERIMENTAZIONE  
PER L'INDUSTRIA CERAMICA

Bologna, 10/12/2018

*FRIANOVO CERAMIC  
FACTORY LLC  
141147, Russia, MR,  
Shelkovsky Distr.*

## TEST LABORATORY

### TEST REPORT No. 7778/18

Requested by:	FRIANOVO CERAMIC FACTORY LLC 141147, Russia, MR, Shelkovsky Distr.
On (date):	19/10/18
For the sample marked:	"STONE".

**The results reported relate only to the samples tested.**

**No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision.**

**The reproduction of this test report is only authorized in the form of a complete photographic facsimile.**

**Our written approval is necessary for any partial reproduction.**

**This test report consists of 3 pages this cover included.**



CENTRO CERAMICO

Test Report No. 7778/18

Date 10/12/2018

Page 2 of 3

Description of the sample:	Glazed ceramic tiles 60 x 60 x 1.1 cm marked "STONE".
Manufacturer:	-----
Sampling details	
- Where:	-----
- Date:	-----
- By whom:	CUSTOMER
- How (methods):	-----
Date of receipt in laboratory:	05/11/18

TESTS PERFORMED :

		Date of starting	Date of ending
<input checked="" type="checkbox"/>	DIN 51097 (92) Slip resistance	03/12/18	03/12/18




**DIN 51097 (92) - Slip resistance**

- Size of the tested surface (m) 0.50 x 1.00
- Joint width (mm): -----
- Grout: -----

**OPERATIVE CONDITIONS**

Fixing scheme



**RESULTS**

- Average slip angle:

21°

**CLASSIFICATION (BGI/GUV-I 8527- 2010)**

- Evaluation group:

A+B

P  
Pietro Bruzzi  
Technical verification



Prof. Maria Chiara Bignozzi

Director